

## EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L3	514	359/652,654.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/05/15 10:46
L4	154	L3 and layers	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/05/15 10:46
L5	6	359/652.ccls. and layer same thickness same (wavelength wave adj length)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/05/15 10:46
L7	22	(gradient graded) near3 (refractive index indice) and silicon adj dioxide and tantalum adj pentoxide	USPAT	OR	ON	2006/05/15 10:46
L8	44	(tantalum adj pentoxide "ta.sub.2o") and (silicon adj dioxide "sio.sub.2") and (gradient graded) near3 index	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/05/15 10:47